

Cement Test Certificate

Final

Product Certified: Type HE Brightonlite Cement
Test Certificate Number: 210450
Produced At: Adelaide Brighton Cement, Angaston Plant, SA
Sample Code: B088ba1
Sample Date: 01/11/2021

Nominal Blend	Requirements	Result
Clinker		>85 %
Ground Granulated Iron Blast-Furnace Slag		Nil
Mineral Addition	Max 7.5 %	<7.5 %
Calcium Sulphate		>4 %
Minor Additional Constituents	Max 5 %	Nil

Reportable Property	Test Method	Requirements of AS3972	Result
3 Day Strength	AS2350.11	Min 25.0 MPa	43.4 MPa
7 Day Strength	AS2350.11	Min 40.0 MPa	51.2 MPa
28 Day Strength	AS2350.11	N/R	60.0 MPa
Initial Set Time	AS2350.4	Min 45 min	90 min
Final Set Time	AS2350.4	Max 360 min	150 min
Soundness	AS2350.5	Max 5 mm	0 mm
Sulfuric Anhydride content (SO ₃)	AS2350.2	Max 3.5 %	2.6 %
Chloride Ion	AS3583.13	Max 0.10 %	0.002 %

Other Properties

SiO ₂	AS2350.2	N/R	20.6 %
Al ₂ O ₃	AS2350.2	N/R	4.8 %
Fe ₂ O ₃	AS2350.2	N/R	0.6 %
CaO	AS2350.2	N/R	64.7 %
MgO	AS2350.2	N/R	0.9 %
Na ₂ O Equivalent	AS2350.2	N/R	0.3 %
Loss on Ignition	AS2350.2	N/R	4.3 %
Fineness Index	AS2350.8	N/R	430 m ² /kg
Normal Consistency	AS2350.3	N/R	29.8 %
Brightness (L)*	BH-TM-0552	N/R	72

This document shall not be reproduced except in full.

REMARKS

These test result apply specifically to the sample as received at the Adelaide Brighton Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.


This despatch grab sample complies to the requirements of AS3972:2010, Type HE Cement.

* NATA Accreditation No 252 does not cover the performance of this service.

N/R = No Requirement



Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.



Approved Signatory

M. Wythe

Issue Date: 17/12/2021