

Quicklime Test Certificate

Final

Product Certified: Quicklime
Test Certificate Number: 220161
Produced At: Adelaide Brighton Cement, Angaston Plant, SA
Sample Code: A083f56
Sample Date: 01/02/2022

Reportable Property	Test Method	Requirements of AS1672.1	Result
CHEMICAL ANALYSIS			
Available Lime (CaO)	AS4489.6.1	Min 60 %	87.5 %
Magnesium Oxide	AS4489.5.1	N/R	1.1 %
Calcium Oxide	AS4489.5.1	N/R	92.9 %
Loss On Ignition	AS4489.7.1	N/R	3.0 %
Carbon Dioxide	BH-TM-0547	Max 5 %	2.7 %
PHYSICAL TESTING			
Temperature Rise in 30 seconds	AS4489.3.1	N/R	18 °C
Total Temperature Rise	AS4489.3.1	N/R	47 °C
Total Slaking Time	AS4489.3.1	N/R	12 min
600 µm Residue on Slaking	AS4489.3.1	Max 20 %	0.1 %


This document shall not be reproduced except in full.

REMARKS

These test result apply specifically to the sample as received at the Adelaide Brighton Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.
 This despatch grab sample complies to the requirements of AS1672.1:1997, Quicklime.
 N/R = No Requirement



Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this documt are traceable to Australian/national standards.



Approved Signatory

M. Wythe

Issue Date: 17/05/2022