

# Cement Test Certificate

Final

**Product Certified:** Type HE Brightonlite Cement  
**Test Certificate Number:** 230177  
**Customer:** Adelaide Brighton Cement, Angaston Plant, SA  
**Sample Code:** B099639  
**Sample Date:** 06/03/2023

Nominal Blend	Requirements	Result
Clinker		>85 %
Ground Granulated Iron Blast-Furnace Slag		Nil
Mineral Addition	Max 7.5 %	<7.5 %
Calcium Sulphate		>4 %
Minor Additional Constituents	Max 5 %	Nil

Reportable Property	Test Method	Requirements of AS3972	Result
3 Day Strength	AS/NZS2350.11	Min 25.0 MPa	41.1 MPa
7 Day Strength	AS/NZS2350.11	Min 40.0 MPa	49.1 MPa
28 Day Strength	AS/NZS2350.11	N/R	59.9 MPa
Initial Set Time	AS/NZS2350.4	Min 45 min	105 min
Final Set Time	AS/NZS2350.4	Max 360 min	135 min
Soundness	AS/NZS2350.5	Max 5 mm	1 mm
Sulfuric Anhydride content (SO <sub>3</sub> )	AS2350.2	Max 3.5 %	2.5 %
Chloride Ion	AS3583.13	Max 0.10 %	0.001 %

**Other Properties**

SiO <sub>2</sub>	AS2350.2	N/R	20.8 %
Al <sub>2</sub> O <sub>3</sub>	AS2350.2	N/R	4.8 %
Fe <sub>2</sub> O <sub>3</sub>	AS2350.2	N/R	0.6 %
CaO	AS2350.2	N/R	65.4 %
MgO	AS2350.2	N/R	0.9 %
Na <sub>2</sub> O Equivalent	AS2350.2	N/R	0.3 %
Loss on Ignition	AS2350.2	N/R	3.9 %
Fineness Index	AS/NZS2350.8	N/R	455 m <sup>2</sup> /kg
Normal Consistency	AS/NZS2350.3	N/R	28.6 %
Brightness (L)*	BH-TM-0552	N/R	72

*This document shall not be reproduced except in full.*

**REMARKS**

These test result apply specifically to the sample as received at the Adelaide Brighton Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.


This despatch grab sample complies to the requirements of AS3972:2010, Type HE Cement.

\* NATA Accreditation No 252 does not cover the performance of this service.

N/R = No Requirement



Accredited for compliance with ISO/IEC  
 17025 - Testing.



Approved Signatory

M. Wythe

**Issue Date:** 12/05/2023