

Final

Product Certified: Quicklime
Test Certificate Number: 240130
Customer: Adbri Cement, Angaston Plant, SA
Sample Code: A089580
Sample Date: 02/02/2024

Reportable Property	Test Method	Requirements of AS1672.1	Result
CHEMICAL ANALYSIS			
Available Lime (CaO)	AS4489.6.1	Min 60 %	87.5 %
Magnesium Oxide	AS4489.5.1	N/R	1.1 %
Calcium Oxide	AS4489.5.1	N/R	93.7 %
Loss On Ignition	AS4489.7.1	N/R	1.7 %
Carbon Dioxide	BH-TM-0547	Max 5 %	2.1 %
PHYSICAL TESTING			
Temperature Rise in 30 seconds	AS4489.3.1	N/R	12 °C
Total Temperature Rise	AS4489.3.1	N/R	46 °C
Total Slaking Time	AS4489.3.1	N/R	13 min
600 µm Residue on Slaking	AS4489.3.1	Max 20 %	<0.1%

This document shall not be reproduced except in full.

REMARKS


These test result apply specifically to the sample as received at the Adbri Cement Birkenhead Laboratory (Accreditation number: 252), 62 Elder Rd Birkenhead SA 5015.

This despatch grab sample complies to the requirements of AS1672.1:1997, Quicklime.

N/R = No Requirement



Accredited for compliance with ISO/IEC
17025 - Testing.



Approved Signatory

M. Wythe

Issue Date: 08/03/2024