

PRODUCT DESCRIPTION

Adbri EvoCem™ is a Type GL cement conforming to Australian Standard AS 3972-2010 as a general purpose limestone cement. EvoCem™ reduces the embodied carbon of cement by up to 8% compared to Adbri's Birkenhead Type GP cement, as verified in Adbri's Cement EPD.

EvoCem™ is manufactured to exacting standards at our Birkenhead works in Adelaide, South Australia. Adbri EvoCem™ is suitable for use in the construction and building industry, and domestic applications.

SUPPLY

EvoCem™ is available in bulk from the Birkenhead works.

SPECIFICATION

Adbri EvoCem™ exceeds the minimum specification for Type GL cement given in AS 3972.

EvoCem™ is manufactured under a third party certified manufacturing and supply quality assurance system to ISO 9001 (BSI Certification No FS 604665).

EvoCem™ is produced from Portland cement clinker, gypsum, limestone, and may contain between 8 % and 20 % limestone as a mineral addition.

APPLICATIONS

EvoCem™ is ideal as a Type GP cement alternative in structural and general concrete applications, as a general binder for soil stabilization, and in cement based products.

Supplementary cementitious materials (SCM's):

EvoCem™ is compatible with fly ash, amorphous silica, and ground granulated blast furnace slag conforming to the relevant sections of AS 3582.

Admixtures for concrete:

EvoCem™ is compatible with concrete admixtures complying with AS 1478.

TYPICAL PROPERTIES

Adbri EvoCem™ typically has lower associated carbon emissions from its manufacture compared to a Type GP cement, while maintaining similar performance properties to Type GP cement.

Typical physical properties

Test	Typical values	AS 3972 requirements
Fineness index (m ² /kg) AS 2350.8		
	380 - 450	-
Setting time (min) AS 2350.4		
Initial	126	Min 45
Final	180	Max 600
Soundness (mm) AS 2350.5		
	0 - 1	Max 5
Compressive strength ISO-CEN mortar bars (MPa) AS 2350.11		
3-day	29 - 45	-
7-day	39 - 55	Min 20
28-day	53 - 65	Min 35

Typical chemical properties

Test	Units	Typical values	AS 3972 Max
Sulphur trioxide	%	2.2 – 3.0	3.5
Loss on ignition	%	5 – 8	-
Chloride	%	0.01 – 0.06	0.1
Equivalent alkalis	%	0.37 – 0.49	-
Hexavalent chromium	mg/kg	Trace	-
Crystalline silica	%	Trace	-
Components:			
Portland clinker	%	73 – 87	-
Gypsum	%	5 – 7	-
Mineral addition	%	8 – 20	20

HANDLING AND STORAGE

Transportation may be in bulk road or rail tankers.

EvoCem™ can be stored in concrete or steel silos, and bags for up to six months; provided protection against ingress of moisture is not observed throughout the storage of the product. To achieve optimum results, ideally use within 3 months of purchase.

Ingress of moisture can occur due to rain, liquid spillage (on or around the product) or a high humidity climate. Such exposure will degrade the performance of the product.

Do not use if the product has become hard or lumpy.

SAFETY INFORMATION

For safety information refer to the safety datasheet for Adbri EvoCem™.

CONTACT POINTS

For further information contact the Sales and Marketing department at:

Adelaide Brighton Cement Ltd
t/a Adbri Cement SA
ABN 96 007 870 199
62 Elder Road
BIRKENHEAD SA 5015

Telephone: 08 8300 0300

Website: www.adbricement.com.au

DISCLAIMER

While the information in this product datasheet has been prepared in good faith, Adelaide Brighton Cement Limited does not warrant that the information is accurate, complete, or up to date.

Each user of any information, or any product referred to, in this product datasheet must:

- Determine whether the information or product is suitable for their purpose;
- Assess and control any risks associated with the information or product; and
- Obtain professional advice in relation to the use of the information or product.

Failure to do so may result in serious damage or injury.

To the extent permitted by law, Adelaide Brighton Cement Limited:

- Excludes all representations, warranties, and guarantees in relation to any information in this product datasheet; and
- Will not be liable for any direct, indirect, consequential, incidental, special, or economic loss (including, but not limited to any loss of actual or anticipated profits, revenue, savings, production, business, opportunity, access to markets, goodwill, reputation, publicity, or use) arising from any use of or reliance on any information in this product datasheet.